



Degreasing 1018

Electrolytic degreaser as well as soak cleaner

This silicate and cyanide free salt mixture is designed for the electrolytic degreasing and activation of iron, copper and brass. This product contains chelating agents, which dissolve oxides and makes the ready degreasing insensitive against water hardness. Instead of silicates there are other builders to get high dirt dispersing ability.



Properties and benefits

- Free of silicates
- Free of cyanides
- Good oxide solubility

Application area

- Iron, copper, brass, zinc
- Electrolytic degreasing
- Soak clean

our know-how
is your success

iwgplating.com





Technical Data

Electrolyte properties	
Parameter	Range
Temperature electrolytic	20 - 60 °C
Temperature soak cleaner	70 – 95°C
Time of exposition	0,5 - 4 minutes

Products available

2211500	Degreasing 1018 Part 1
2211600	Degreasing 1018 Part 2
2211700	Degreasing 1018 Part 2 M
2211800	Degreasing 1018 Defoamer

FOR ANY FURTHER INFORMATION WE WILL BE PLEASED TO BE AT YOUR DISPOSAL
PERSONALLY UNDER+ 43 (0)2287 71073 OR OFFICE@IWGPLATING.COM