



Degreasing 1070

Electrolytic degreasing

This cyanide free salt mixture is designed for the electrolytic degreasing and activation of iron and copper alloys.

Degreasing 1070 can be used as anodic as well as cathodic degreasing.



Properties and benefits

- Free of cyanides
- Good oil solubility

Application area

- Iron, copper alloys
- anodic degreasing
- cathodic degreasing

our know-how
is your success

iwgplating.com





Technical Data

Electrolyte properties	
Parameter	Range
Temperature	
for copper alloys	20 – 40 °C
for steel	20 – 50 °C
Current density	
for copper alloys	1 – 4 A/dm ²
for steel	4 – 6 A/dm ²

Products available

2222700	Degreasing 1070
2222750	Degreasing 1070 Defoamer

FOR ANY FURTHER INFORMATION WE WILL BE PLEASED TO BE AT YOUR DISPOSAL
PERSONALLY UNDER+ 43 (0)2287 71073 OR OFFICE@IWGPLATING.COM

